

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number  
**WO 2005/017477 A1**

(51) International Patent Classification<sup>7</sup>: **G01K 11/32**,  
1/08, G02B 6/24, 6/24, 1/00

(21) International Application Number:  
PCT/US2003/037303

(22) International Filing Date:  
21 November 2003 (21.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/428,099 21 November 2002 (21.11.2002) US

(71) Applicant (for all designated States except US):  
**TRUSTEES OF BOSTON UNIVERSITY** [US/US];  
One Sherborn Street, Boston, MA 02215 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MORSE, Theodore**,  
F. [US/US]; 127 Bay State Road, Boston, MA 02215 (US).  
**LUO, Fei** [CN/US]; 176 Presidents Lane, Apt. #302,  
Quincy, MA 02169 (US).

(74) Agents: **GAGNEBIN, Charles, L., III** et al.; Weingarten,  
Schurgin, Gagnebin & Lebovici, LLP, Ten Post Office  
Square, Boston, MA 02109 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR,  
CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD,  
GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR,  
KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,  
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU,  
SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,  
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (*regional*): ARIPO patent (BW, GH,  
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE,  
SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA,  
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Declarations under Rule 4.17:**

— as to applicant's entitlement to apply for and be granted  
a patent (Rule 4.17(ii)) for the following designations AE,  
AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ,  
CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE,  
EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN,  
IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,  
MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM,  
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ,  
TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM,  
ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD,  
SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY,

[Continued on next page]

(54) Title: FIBER OPTIC TEMPERATURE SENSOR



(57) Abstract: A fiber optic temperature sensor (10) and system employ optical (fiber 34) and a fiber Bragg grating (36) using non-silica materials that can withstand temperature ranges extending well above the silica-imposed limit of 1,100 degrees C. The system measures the wavelength shift of light reflected from the fiber Bragg grating (36) and converts it into a temperature value. Specific optical fibers include sapphire, which can be used at temperatures approaching 1,800 degrees C, and yttria-stabilized zirconia (YSZ), which can be used at temperature in excess of 2,300 degrees C. One specific grating employs alternating layers of YSZ, with the percentage of yttria varying in the alternating layers to achieve the desired difference of refractive index, and another grating employs alternating layers of alumina and zirconia.